



# STOPAQ® PASTE CZHT

## **Product Information**

**Product description:** Stopaq<sup>®</sup> Paste CZHT is a corrosion preventing moulding paste that is especially designed for high temperature applications. It adheres extremely well to steel and factory applied pipeline coatings like PE, PP and FBE.

Stopaq® Paste CZHT is a non-toxic, cold-applied, and visco-elastic moulding paste, based on a compound consisting of non-crystalline, low-viscosity, non-crosslinked (fully amorphous), non-reactive Polyisobutene.

Stopaq® Paste CZHT is viscous at the indicated operating temperatures. Due to its liquid nature it has a set of unique properties like cold-flow into all irregularities of the substrate and self-healing of the complete coating system. The compound does not cure and is unable to build up internal stress. Stopaq® Paste CZHT is fully resistant to water and has a very low gas- and water vapour permeability.

Stopaq® Paste CZHT requires an additional flexible mechanical protective layer like Stopaq® Outerwrap. This improves impact and indentation resistance of the coating system and supports the self-healing ability of small damages like dents and cuts. Optionally a rigid mechanical protective layer can be applied on top like Stopaq® Polyester or Stopaq® Outerglass Shield.

#### Features:

- Controlled cold flow providing permanent inflow into the finest pores of the substrate
- Conforms to irregular shapes
- Low surface tension; adheres on many types of dry substrates at a molecular level
- · Adhesion based on vanderWaals forces
- · Inert to ageing and weathering
- · No osmosis or underfilm migration of moisture
- · No cathodic disbondment
- Environmentally friendly, no health and safety hazards to humans
- Resistant to many chemicals like water, salts, acids, alkalis, polar solvents, etc. For additional information, please consult Stopaq B.V.

## **Benefits:**

- Easy to apply
- · Easy to control application
- Surface tolerant: no blasting techniques required, wire brushing is sufficient (ISO 8501-1: St 2)
- · Can be moulded onto various types of irregular shaped objects
- Cathodic Protection (CP) of steel structures is not affected
- Guaranteed performance

# **Application examples**

Flanges: For protection against external corrosion and shaping of connection flanges, insulation flanges and blind flanges.

Valves: For protection against external corrosion and shaping of valves.

Irregular shaped parts: For protection against external corrosion and shaping of manhole covers, bolts & nuts, etc.

Cad-welds: For protection against external corrosion of welded CP-wire connections on underground pipelines (Pin-brazes) and underground steel structures protected by CP.

Pipe coating repairs: For protection against external corrosion and as filler for pipeline coating defects of e.g. 3LPE coated pipelines, prior to application of consecutive mechanical protective coating.

B. I. d	( O ) B D ( ) O	71 I T	
	s of Stopaq <sup>®</sup> Paste C	2H I	
Colour	Green		
Density	1.5 g/cm <sup>3</sup>		
Temperature ranges	Service:	- 45°C to +95°C	
	Short term max.:	+120°C	
Water absorption	≤ 0.03% (ASTM D570)		
Glass transition	≤ - 65°C * <sup>)</sup>		
temperature			
Specific electrical	$Rs_{100} > 10^8 \Omega m^2$		
insulation			
resistance			
Adhesion test	Tested @+23°C and @+95°C on steel and PP plant		
	coating *). Results on all substrates:		
	<ul> <li>Coating leaves a film of corrosion preventive</li> </ul>		
	compound on the substrate		
Thermal ageing	Dry ageing 100 days@+115°C and hot water		
resistance and hot	immersion 100 days@+95°C *):		
water immersion	<ul> <li>Results of adhesion test are identical to results</li> </ul>		
	obtained with non-a		
Salt spray	Tested 720 h, 5% NaCl @ + 85°C (ASTM B117):		
resistance	No corrosion detected		

General order information				
Product		Stopaq <sup>®</sup> Paste CZHT is available in sheets,		
		packed in siliconized foil in cardboard boxes.		
	Art. Nr.:	Product dimensions and contents:		
	6142	Sheet 2kg, 6 pcs./box, 288 pcs./pallet		
Handling		Handle with care. Keep boxes upright.		
Storage		Store indoor, clean and dry, away from direct		
		sunlight in a cool place below +45°C.		
		Unlimited shelf life.		

V 4 / 20151005 (EN) Page 1 / 2

Application instru	ction - Job preparation	Application instruction - Brief version		
Tools, equipment and auxiliaries	<ul> <li>Temperature probe, Dew point tester, High voltage holiday tester</li> </ul>	See specific Stopaq coating instructions for e.g. flanges, valves, coating repair, etc.		
	<ul> <li>Scissors, Knife, Measuring tape</li> <li>Abrading pads, Wire brushes</li> <li>SFL Substrate cleaner or Isopropyl alcohol,</li> </ul>	Boundaries in flange application	Apply wraps of Stopaq® Wrappingband CZHT onto the pipe sections underneath and beyond the planned boundaries of Stopaq® Paste CZHT	
Additional coating	cas. nr. 67-63-0  - Heating blanket or other suitable heating device  - Personal protective gear  Depending on type of application, various	Application	Apply lumps of mouldable paste around the shaped objects. Press the paste. Avoid air inclusions. After shaping, the surface should be smooth to enable proper application of additional materials.	
materials	additional materials might be needed:			
	<ul> <li>Stopaq<sup>®</sup> Wrappingband CZHT</li> </ul>	Application instruction - Quality control		
	<ul> <li>Stopaq<sup>®</sup> Outerwrap HTPP</li> <li>Stopaq<sup>®</sup> Polyester</li> <li>Stopaq<sup>®</sup> Outerglass Shield</li> </ul>	Visual inspection	The appearance of Stopaq <sup>®</sup> Paste CZHT must look smooth and tight. Recommended minimum thickness on all details is 20 mm.	
High humidity	Stopaq® Paste CZHT can be applied in a humid atmosphere. The substrate should be free from condensing water which can be reached by keeping the temperature at least 3°C above dew point.	Holiday detection	Immediately after application of Stopaq <sup>®</sup> Paste CZHT, a holiday test should be carried out with a High voltage holiday tester at ≥15 kV. A brush probe is recommended. No further testing is required.	
Work area and	The substrate should be dry, clean and			
substrate	protected against negative weather influences.	Application instruction - Mechanical protection		
Application instru	Stopaq® Paste CZHT should be dry and the temperature should preferably be above +50°C for the ease of application. To achieve this, the sheets can be heated with the heating blanket.  ction - Surface preparation The area to be coated has to be clean, dry, and	Mechanical protection	Once applied, Stopaq® Paste CZHT should be protected against impacts, indentations, soil pressure and other influences by wraps of Stopaq® Outerwrap, optionally followed by Stopaq® Polyester or Stopaq® Outerglass Shield. Mechanical protection should overlap the boundaries of applied Paste CZHT.	
	free from oil, grease and dust. All contamination			
	including mill-scale has to be removed.	Handling and commissioning		
Degreasing	Degrease surfaces with isopropyl alcohol and e.g. a lint-free cloth.	Exposure to loads	Objects coated with Stopaq® Paste CZHT should not be exposed to loads e.g. from supports- or	
Salts and bacteria Condensation of	No need for additional cleaning.  Prior to and during the application, the	Immersion or	lifting equipment.  Immersion or burying is possible immediately	
water	temperature of the substrate(s) must be at least 3°C above the dew point.	burying	after completion of the coating application.  Consult data sheets for specific instructions of	
Substrate temperature	Temperature of the substrate should preferably between +30 and +50°C. Preheating may be required.		additional materials used. Backfill and compact with clean sand and filling material without sharp stones or hard lumps of soil.	
Steel	Minimum requirement for surface preparation is St-2 according to ISO 8501-1. Roughness	Information		
Other substrates	profile is not essential for adhesion.  De-gloss and degrease the surfaces by using an abrasive pad and isopropyl alcohol.	Documentation	Extensive information is available on our website. Application instructions and other	
Final check	The substrates prepared for coating, should be clean, dry and free of dust according to ISO		documentation can be obtained by contacting our head office, from our local distributor or by sending email to <b>info@stopaq.com</b>	
	8502-3, grade 3.	Certified staff	Application of the described coating system	



Seal For Life Industries LLC Franklin, MA, USA Tel: +1 508 918 1600 Toll Free: +1 800 248 7659 Fax:+1 508 918 1905 franklin@sealforlife.com Seal For Life Industries Mexico S de R.L. de C.V. Tijuan, Mexico Tel USA: +1 858 633 9797 Fax USA: +1 858 633 9740 Tel Mx: +52 664 647 4397 Fax Mx: +52 664 607 9105 mexico@sealforlife.com Seal For Life Industries Stopaq B.V. Stadskanaal, the Netherlands Tel: +31 599 696 170 Fax: +31 599 696 177 info@sealforlife.com Seal For Life Industries BVBA Westerlo, Belgium Tel: +32 14 722 500 Fax: +32 14 722 570

should be carried out by certified personnel.

Seal For Life India Private Ltd. Baroda, India Tel: +91 2667 264 721 Fax: +91 2667 264 724

Anodeflex® - Stopaq® - Polyken® - Covalence® - Powercrete® - Sealtaq® - Blockr® - Easy.Qote® - SynergyQ®

DISCLAIMER: Seal For Life Industries warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Seal For Life Industries written instructions. Since many installation factors are beyond the control of Seal For Life Industries, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Seal For Life Industries liability is stated in the standard terms and conditions of sale. Seal For Life Industries makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the left. Stopaq® is a registered trademark of Seal For Life Industries.