

PRODUCT DATA SHEET

STOPAQ® 4100 PUTTY

Product Information

Product description: Stopaq[®] 4100 Putty is a malleable synthetic compound for protection of underground objects against external corrosion. It is used for filling of voids and leveling of irregular surfaces, prior to application of Stopaq[®] coating materials.

Stopaq[®] 4100 Putty is a non-toxic material, suited for application on steel pipelines, fittings, and adjacent factory coatings like PE, PP, FBE, etc. It is fully resistant to water and has a very low permeability. It is designed for use on buried structures with low to medium service- and ambient temperatures. The compound does not cure and will not build-up internal stresses. Objects coated with Stopaq[®] 4100 Putty should be protected against mechanical impacts and indentation by covering it with a protective layer of Stopaq[®] Geotextile and Stopaq[®] Outerwrap.

Features:

- Adheres on many types of dry substrates.
- Minor surface preparation required wire brushing to St 2 cleanliness (ISO 8501-1) is sufficient, abrasive blast cleaning is not required.
- Fills the finest pores of the substrate
- No effect on Cathodic Protection

Benefits:

- Harmless to environment and workers
- Cost- and time saving surface preparation
- No primer required
- · Fast and easy to apply
- Malleable putty, easy to mold on irregular shaped objects
- · Can be re-used no waste

Product certificate: Stopaq[®] 4100 Putty is certified according to KIWA BRL-K911/02:

"Kiwa Product certificate for corrosion protection compound and tapes for tank and pipeline installations according to the Evaluation Guideline BRL-K911/02 with a verification according to standard EN-12068."

Application examples

Flanges: For protection against external corrosion and shaping of buried pipe flanges, insulation flanges and blind flanges.

Valves: For protection against external corrosion and shaping of buried valves.

Manhole covers: For protection against external corrosion and shaping of buried manhole covers, bolts & nuts, etc.

Product properties of Stopaq® 4100 Putty				
Colour	Green			
Density	1.2 – 1.5 g/cm³ (ISO 1183-1)			
Temperature range	Operational: -10°C to +30°C			
Specific electrical insulation resistance	> 10 ⁸ Ω.m² (EN 12068) ^{A)}			
Shape retention	< 4mm @ +30°C (NEN 6910) A)			
Water absorption	< 0.07% ^{A)}			
Vitrification	No changes @ -10°C to +30°C A)			
temperature				
Adhesion	> 30N / 10 cm ^{2 A)}			
Resolved shear stress	> 400 Pa @ +30°C ^{A)}			

A) according to KIWA BRL-K911/02

General order information			
Product		Stopaq® 4100 Putty is available in different	
		packing sizes	
<u>A</u>	rt. Nr.:	Packing size	
	4110	Cartridge 0.53 kg, 20 pcs/box, 720 pcs/pallet	
	4125	Bag 2 kg, 9 pcs/box, 324 pcs/pallet	
Handling		Handle with care. Keep boxes upright.	
Storage		Store indoor, clean and dry, away from direct	
		sunlight in a cool place below +30°C.	
		Unlimited shelf life.	

V 6 / 20171124 (EN) Page 1 / 2

Application instru	ction - Job preparation	Application instru	ction – Brief version
Tools, equipment	Temperature probe, Dew point tester, High	General	Specific instructions are available for various
and auxiliaries	voltage holiday tester - Caulking gun with flexible nozzle		applications of Stopaq [®] 4100 Putty. Please contact Stopaq B.V. for further information.
		Coating	Certain applications require that Stopaq®
	 Scissors, Knife, Measuring tape 	boundaries	Wrappingband CZ or CZH is applied adjacent to
	 Abrasive pads, Wire brushes 	boundaries	the planned boundaries of Stopag [®] 4100 Putty.
	 SFL[®] Substrate Cleaner. Alternatively 		
	Isopropyl alcohol (cas. nr. 67-63-0)		See specific coating instructions for more
	 Personal protective gear 	Amuliantian	information.
Additional coating	Depending on type of application, various	Application	Apply a small amount of Stopaq® 4100 Putty on
materials	additional mechanical protective materials might		an abrading pad and rub it onto the surfaces to
	be needed:		be protected. When all surfaces are covered with a thin layer
	 Stopaq[®] Wrappingband CZ or CZH 		
	 Stopaq[®] Geotextile 		of 4100 Putty, continue with building up, molding
	 Stopaq[®] Outerwrap (various types 		and shaping. Avoid air enclosures. The shaped
	available)		surface should be smooth, suited for covering
	 Optional additional mechanical protection: 		with additional Stopag® coating materials.
	Stopaq [®] Outerglass Shield XT Grey or	Reinforcement	In case the layer thickness of Stopaq® 4100
	Stopaq® Polyester		Putty exceeds 20mm, it is recommended to
High humidity	Stopaq® 4100 Putty can be applied in a humid		apply a reinforcement interlayer web for
	atmosphere. The substrate should be free from		stabilization of the molded putty layer.
	condensing water which can be reached by	Mechanical	Stopaq® 4100 Putty should be protected against
	keeping the temperature at least 3°C above dew	protection	mechanical forces, like impact and indentation,
	point.		by application of Stopaq® Geotextile and
Work area and	The work area and substrates should be dry,		Stopaq® Outerwrap. Mechanical protection
substrate	clean and protected against negative weather		should overlap the boundaries of applied Putty.
substrate	influences.		Optionally, Stopaq® Outerglass Shield XT Grey
Draduat canditions	Stopaq® 4100 Putty should be dry and the	1	or Stopaq [®] Polyester can be installed for
Product conditions	temperature should preferably be between.		additional mechanical protection.
		Visual inspection	The appearance of Stopaq® 4100 Putty must
	+20°C and +25°C for the ease of application.	Ц	look smooth and tight and should cover all
			details with a thickness of at least 20 mm.
	ction - Surface preparation	Holiday detection	Immediately after application of Stopaq® 4100
General	The area to be coated has to be clean, dry, and		Putty, a holiday test should be carried out with a
	free from oil, grease and dust. All contamination		High Voltage holiday tester at ≥15 kV. A brush
	including mill-scale has to be removed.		probe is recommended. No further testing is
Degreasing	Degrease surfaces with SFL® Substrate		required.
	Cleaner and e.g. a lint-free cloth.		
Preventing	Prior to and during the application, the	Handling and com	nmissioning
condensation of	temperature of the substrate(s) must be at least	Exposure to loads	Objects coated with Stopaq® 4100 Putty should
water	3°C above the dew point.		not be exposed to loads e.g. from supports- or
Substrate	Temperature of the substrate should preferably		lifting equipment.
temperature	be between +20°C and +30°C for fast and easy	Immersion or	Immersion or burying is possible immediately
	application. Preheating may be required.	burying	after completion of the coating application.
Steel	Minimum requirement for surface preparation is		Consult data sheets for specific instructions of
	St 2 according to ISO 8501-1. Roughness profile		additional materials used. Backfill and compact
	is not essential for adhesion.		with clean sand and filling material without sharp
Bitumen	Remove loose bitumen. For proper adhesion,		stones or hard lumps of soil.
	make sure that the surface is clean and dry. The		States of Hara lamps of John
	product must not be applied on moist bitumen.	Information	
	Moderate heating of bitumen is recommended in	Information	
	order to let trapped water evaporate. After this,	Documentation	Extensive information is available on our web-
	bitumen should be allowed to cool to preferred		site. Application instructions and other
	substrate temperature.		documentation can be obtained by contacting
Other substrates	De-gloss and degrease the surfaces by using an		our head office, from our local distributor or by
	a base has a selected OFL® Outstand OFL®		sending email to info@stopaq.com
	aprasive pag and SEL Substrate Cleaner		
Final check	abrasive pad and SFL® Substrate Cleaner The substrates prepared for coating should be	Certified staff	Application of the described coating system
Final check	The substrates prepared for coating should be clean, dry and free of dust according to ISO	Certified staff	



Seal For Life Industries LLC Franklin, MA, USA Tel: +1 508 918 1600 Toll Free: +1 800 248 7659 Fax:+1 812 250 0834 franklin@sealforlife.com

8502-3, grade 3.

eal For Life Industries Mexic S de R.L. de C.V. Tijuana, Mexico Tel USA: +1 858 633 9797 Fax USA: +1 858 633 9740 Tel Mx: +52 664 647 4397 Fax Mx: +52 664 607 9105 mexico@sealforlife.com

Seal For Life Industries Stopaq B.V. Stadskanaal, the Netherlands Tel: +31 599 696 170 Fax: +31 599 696 177 info@sealforlife.com

Westerlo, Belgium Tel: +32 14 722 500 Fax: +32 14 722 570

Baroda, India
Tel: +91 2667 264 721
Fax: +91 2667 264 724
india@sealforlife.com

 $Anodeflex^{\texttt{w}} - Stopaq^{\texttt{w}} - Polyken^{\texttt{w}} - Covalence^{\texttt{w}} - Powercrete^{\texttt{w}} - Sealtaq^{\texttt{w}} - Blockr^{\texttt{w}} - Easy.Qote^{\texttt{w}} - SynergyQ^{\texttt{w}} - Protecta-mesh^{\texttt{w}}$

DISCLAIMER: Seal For Life Industries warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the technical data sheet when used in compliance with Seal For Life Industries' written instructions. Because many installation factors are beyond the control of Seal For Life Industries, the user shall determine the suitability of the products for the intended uses and assume all risks and liabilities in connection herewith. Seal for Life's liability is stated in its General Terms and Conditions of Sale. Seal For Life Industries makes on other warranty either express or implied. All information contained in this technical data sheet is to be used as a guide and is subject to change without notice. This technical data sheet supersedes all previous data sheets on this product. Seal For Life Industries is a registered marks of the Berry Global Group, Inc. or its affiliates.