

# STOPAQ<sup>®</sup> 4200 FILLER

## **Product Information**

Generic type: Non-toxic, single component, non-thermosetting injection filler. Stopaq<sup>®</sup> 4200 Filler has excellent adhesion- and penetration properties, a wide service temperature range, and is fully resistant to water.

Product description: The corrosion preventing, non-curing, surface tolerant Stopaq® 4200 Filler is designed for filling and protecting hard-to-clean or non-cleaned corrosion sensitive areas in narrow, difficult to access spaces such as gaps between flanges, around bolt threads in bolt holes, tank chime areas and around flange seals where water can accumulate. The material is suited for application with a hand operated, electric or pneumatic caulking gun, equipped with a flexible nozzle (supplied by Stopaq®), does not cure and is unable to build-up internal stresses. Due to the permanent viscous properties, Stopaq® 4200 Filler will during time, tend to flow out of the filled spaces. Therefore the filled gaps should be covered with additional Stopaq® materials such as Stopaq® Wrappingband CZH or Stopaq® Wrappingband EZ. For above ground flange application, additional mechanical protection should be installed, e.g. Stopaq® Flangebelt, Stopaq® Polyester, or UV-resistant Stopaq® Outerwrap PVC.

#### Features:

- · Adheres on all dry substrates
- · Easy to apply by injection tool (available separately)
- Surface tolerant
- Permanently fills the finest pores
- Resistant to temperatures down to -45°C
- Non-toxic
- Seals and stops active corrosion
- Blocks H2S gas
- Compatible with various types of existing coatings

### Benefits:

- · Harmless to environment and workers
- Permanent sealing of narrow spaces
- No special surface preparation and primers needed
- Cost- and time saving
- Unlimited shelf life and pot life
- Very long service life

Product certificate: Stopaq<sup>®</sup> 4200 Filler is certified according to KIWA BRL-K911/02:

"Kiwa Productcertificate for corrosion protection compound and tapes for tank and pipeline installations according to the Evaluation Guideline BRL-K911/02 with a verification according to standard EN-12068."

## **Application examples**

**Between flanges:** Injection into the narrow spaces between flanges. Also flowing into the bolt holes, protecting the bolt threads and -shafts against corrosion.

Flange gaskets - External: Corrosion prevention of the outer rims of gaskets in flange fittings.

Storage tanks – Chime area: Protection of steel surfaces in gaps between the tank skirts and the concrete foundations.

**Bolt connections:** For protection of bolt threads and shafts in deep bolt holes (in steel as well as concrete constructions).

Product properties Stopaq® 4200 Filler				
Colour	Green			
Density	1.2 – 1.5 g / cm³ (NEN 1833)			
Temperature	Service:	- 45℃ to + 100℃		
ranges	During application			
	<ul> <li>Substrate temp.:</li> </ul>	- 10℃ to + 60℃		
Specific electrical	> 10 <sup>8</sup> Ω.m <sup>2</sup> (EN 12068)			
resistance*				
Water absorption*	< 0.07% (ASTM D570)			
Vitrification	No changes @ -10℃ to +30℃			
temperature*				
Adhesion*	> 30 N / 10 cm <sup>2</sup>			
	Cohesive fracture on steel, PP, PE and FBE			
	No adhesive failure			
Resistance to	No change in properties (EN 12068)			
thermal ageing*				
Resolved shear	> 400 Pa @ +30℃			
stress*				
UV-resistance*	Tested @ 17.5 GJ/m² (EN 12068):			
	No change in properties			
Salt spray	Tested 720 h, 5% NaCl @ + 85℃ (ASTM B117):			
resistance	No corrosion detected			

<sup>\*</sup> according to KIWA BRL-K911/02

General order information				
Product:	Stopaq <sup>®</sup> 4200 Filler is available in various			
		packing sizes:		
	Art. Nr.	Packing size		
	4210	Cartridge 0.53 k,; 20 pcs/box, 720 pcs/pallet		
	4225	Bag 2 kg, 9 pcs/box, 324 pcs/pallet		
Handling		Handle with care, keep boxes upright		
Storage		Store indoor, clean and dry. Storage		
		temperature is not critical.		
		Unlimited shelf life.		

Ver. 5 / 20111031 (EN) Page 1 / 2

Application instruc	ction: Preparation	Application instru	ction: Brief version
Tools, equipment and auxiliaries	<ul> <li>Caulking gun with 200 mm flexible nozzle</li> <li>Application set for caulking gun</li> <li>Measuring tape</li> <li>Putty knife (blade width 25 – 40 mm)</li> <li>Abrading pads, Scotch-brite type</li> <li>Tube brush Ø 25 mm</li> <li>Masking tape, width 25 mm</li> <li>Personal protective gear like gloves, safety</li> </ul>	Caulking gun preparation Injection	Just prior to application, insert a pre-heated cartridge into the caulking gun. Apply the flexible nozzle at the opening of the cartridge.  Shape the flexible nozzle in order to fit it into the gap to be filled. Push the nozzle as deep as possible into the gap and start injection of the 4200 Filler. Avoid air enclosures by keeping the tip of the nozzle in contact with already injected 4200 Filler. Gently pull out the nozzle while
Additional materials	goggles  Depending on type of application, various additional materials might be needed:  Stopaq® Wrappingband CZH  Stopaq® Outerwrap PVC  Stopaq® Polyester  Stopaq® Wrappingband EZ  Stopaq® Flangebelt	Levelling and smoothening  Application of covering materials	injecting. When the 4200 Filler becomes visible at the boundaries of the opening, the gap is filled completely.  Use the putty knife for smoothening the surface and removal of excess filler. Remove the masking tape afterwards.  Dimensions of covering materials should be sufficient to cover at least 50 mm of the adjacent
Work area and substrate	Stopaq® 4200 Filler can be applied in a humid atmosphere. The surface of the substrate however, should be free from condensing water which can be reached by keeping the temperature at least 3°C above dew point.  The substrate surface should be dry, clean and protected against negative weather influences.		substrate on all sides of the filled gap. In case of flange applications, the gap should be covered with Stopaq® Wrappingband CZH and additionally Stopaq® Flangebelt or Stopaq® Outerwrap PVC. In case of tank chime area, the gap should be covered with Stopaq® Wrappingband EZ
Product conditions	Stopaq <sup>®</sup> 4200 Filler should be dry and have a temperature between + 20℃ to + 40℃ for the ease of application. To achieve this, the cartridge can be placed in e.g. lukewarm water for 15 minutes.	Visual inspection	For other applications, please contact Stopaq b.v.  The 4200 Filler and the covering materials must look smooth and tight and should be shaped around all details and into corners.

Application instru	uction: Surface preparation	Bringing into serv	rice
General	The area to be coated has to be clean, dry, and free from oil, grease, dust, poorly adhering old coating and loose particles. Several methods are	Exposure to loads	Objects filled with Stopaq® 4200 Filler should not be exposed to loads from supports- or lifting equipment.
	suitable for cleaning purposes e.g. by scraping, wire brushing, high-pressure water jetting, vacuum cleaning, compressed air, etc.	ater jetting,	Areas filled with Stopaq® 4200 Filler are fully protected against corrosion from the moment of application and can be commissioned
Degreasing	Degrease surfaces with isopropyl alcohol (cas. nr. 67-63-0)		immediately after completion of application.
Salts and bacteria	No need for additional cleaning	Stopag <sup>®</sup> information	
Condensation of water	Prior to and during the application, the temperature of the substrate(s) must be at least 3°C above the dew point to avoid condensation of water.	Documentation	Extensive information is available on our website. Application instructions, "Stopaq® Technical Standard" and other documentation can be obtained from our head office, from our local
Steel substrate	Clean the surfaces thoroughly by scraping, brushing, vacuum cleaning, etc. in order to remove loose particles (e.g. corrosion) as much as possible.	Certified staff	distributor or by email to info@stopaq.com The application of Stopaq® sealing systems should always be carried out by certified personnel.
Masking	In order to keep surrounding surfaces clean e.g. for application of additional Stopaq® materials, it is recommended to apply masking tape on these surfaces prior to application of Stopaq® 4200 Filler.	Stopaq <sup>®</sup> performance	Extensive laboratory tests and more than 10 years of service in extreme wet and chemical aggressive environments have proven that corrosion, bacterial growth or stress corrosion cracking cannot develop on substrates sealed
Visual inspection	The substrates should be clean, dry and free of dust prior to application		with Stopaq <sup>®</sup> sealing systems.



DISCLAIMER: To the best of our knowledge, the technical data contained herein is true and accurate on the date of publication and is subject to change without prior notice. User must contact Stopaq B.V. to verify correctness before specifying and ordering. No guarantee of accuracy is given or implied. We do not accept any responsibility for coverage, performance or injuries resulting from use. Liability, if any, is replacement of products. No other warranty or guarantee of any kind is made by Stopaq B.V., express or implied, statutory, by operation of law, or otherwise, including merchantability and fitness for a particular purpose. Stopaq® is a registered trademark of Stopaq B.V.

Ver. 5 / 20111031 (EN) Page 2 / 2